

schedule 160 for Plain-End Pipe
(Data from ASME B36.10 (incorporating ASTM A53 Table 2.2))

DN	NPS	Outside Diameter		Wall Thickness		Plain End Mass		Identification	Schedule No.
		mm	in	mm	in	kg/m	lb/ft		
15	1/2	21.3	0.840	4.78	0.188	1.95	1.31		160
20	3/4	26.7	1.050	5.56	0.219	2.90	1.95		160
25	1	33.4	1.315	6.35	0.250	4.24	2.85		160
32	1 1/4	42.2	1.660	6.35	0.250	5.61	3.77		160
40	1 1/2	48.3	1.900	7.14	0.281	7.25	4.86		160
50	2	60.3	2.375	8.74	0.344	7.14	7.47		160
65	2 1/2	73.0	2.875	9.53	0.375	14.92	10.02		160
80	3	88.9	3.500	11.13	0.438	21.35	14.34		160
100	4	114.3	4.500	13.49	0.531	33.54	22.53		160
125	5	141.3	5.563	15.88	0.625	49.12	32.99		160
150	6	168.3	6.625	18.26	0.719	67.57	45.39		160
200	8	219.1	8.625	23.01	0.906	111.27	74.76		160
250	10	273.0	10.750	28.58	1.125	172.27	115.75		160
300	12	323.8	12.750	33.37	1.312	238.69	160.42		160
350	14	355.6	14.000	35.71	1.406	281.72	189.29		160
400	16	406.4	16.000	40.49	1.594	365.38	245.48		160
450	18	457	18.000	45.24	1.781	459.39	308.79		160
500	20	508	20.000	50.01	1.969	564.85	379.53		160
550	22	559	22.000	53.98	2.125	672.30	451.49		160
600	24	610	24.000	59.54	2.344	808.27	542.64		160